



Jet-melt™

Self-Extinguishing Hot Melt Adhesive

3748 VO

Technical Data

February, 2003

Product Description

3M™ Jet-melt™ 3748 VO is a tough, flexible, thermoplastic hot melt, 100% solids adhesive which exhibits good peel adhesion and thermal shock properties along with higher heat resistance. It features excellent electrical properties which make it ideal for use on printed wiring board and other electronic bonding applications.

Jet-melt 3748 VO is self-extinguishing and has a UL 94 VO rating. In addition to electronic applications, it is also useful in many general industrial bonding and sealing applications where a self-extinguishing characteristic is required.

Features

- Excellent Adhesion
- Good Electrical Properties
- Non Corrosive to Metal

Typical Physical Properties

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Base Resin:	Polyolefin
Color:	Light Yellow
Specific Gravity:	1.09
Ball and Ring Softening Point:	305°F (152°C)
Viscosity: @ 356°F (180°C) @ 392°F (200°C) @ 428°F (220°C)	8,500 cps 5,000 cps 3,300 cps
UL 94 (Flammability Classification): UL 1410 (Insulating Material For TV Set):	V-O Per file E61941
Shore D Hardness (ASTM D 2240):	26 @ 77°F (25°C)
Suggested Application Equipment: – 3M™ Polygun™ TC or TCQ Applicator – 3M™ Polygun™ EC - Temperature Module #4 – 3M™ Polygun™ II Applicator	

3M™ Jet-melt™
Self-Extinguishing Hot Melt Adhesive
 3748 VO

Typical Performance Properties

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Two Pound Dead Load Heat Resistance (3M TM C 3093) ⁽¹⁾	175°F (79°C)
Overlap Shear Strength @ 70°F (21°C) (3M TM C 3096) ⁽²⁾ FR-4 to FR-4 Fir to Fir Polypropylene to Polypropylene Polyethylene to Polyethylene	215 psi 275 psi 250 psi 220 psi
180° Peel Adhesion (3M TM C 3168) ⁽¹⁾ Wire Mesh to FR-4 to PP to PE to Fir	38 piw 35 piw 27 piw 26 piw
Weight Loss by TMA (In Air) Temperature of weight loss at 5°C/min	1% @ 459°F (237°C) 5% @ 621°F (327°C) 10% @ 673°F (356°C)
Thermal Coefficient of Expansion by TMA Over -100 to -40°C temperature range Over -20 to 25°C temperature range	-34.0 x 10 ⁻⁶ units/units/°C 154.5 x 10 ⁻⁶ units/units/°C
Thermal Conductivity (@ 41°C [107°F] on .020" samples) BTU-ft./ft ² -hr. - °F Cal./sec. - cm - °C Watt/m - °C J/cm - sec - °C	1.11 x 10 ⁻¹ 4.58 x 10 ⁻⁴ 1.92 x 10 ⁻¹ 1.92 x 10 ⁻³
Thermal Shock Resistance Potted Washer Olyphant test (3M TM C3167) + 100°C (air) to -40°C (liquid)	Passes 5 cycles w/o cracking

- (1) 1" x 4" Douglas Fir specimens are bonded with hot melt adhesive using a 1" overlap shear configuration. Bonds are then conditioned for 24 hours at 70°F (22°C), 50% relative humidity before testing. Bonds are subjected to 2 lbs. per square inch load at 100°F (49°C) for 30 minutes. Temperature of the bond line is raised every 30 minutes until failure. Heat resistance recorded is the last temperature prior to bond failure.
- (2) 1" x 4" Douglas Fir specimens are bonded with hot melt adhesive using a 1" overlap and 13 mil wire spacer to set bond line thickness. Bonds are then conditioned for 24 hours at 70°F (22°C), 50% relative humidity before testing. Bonds are pulled in shear at a separation bond speed of 2 inch a minute recording strength at failure.
- (3) Test involves bonding .020" wire mesh (galvanized window screen type) to substrate using hot melt adhesive. Wire mesh is encapsulated with adhesive. After conditioning, bond is tested by 180° peel back method using Instron at 10 inches per minute peel speed.

3M™ Jet-melt™
Self-Extinguishing Hot Melt Adhesive
 3748 VO

Typical Electrical Properties

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

	100 Hz	1 kHz	10 kHz	100 kHz	1 MHz	100 MHz
Dielectric Constant (ASTM D 150)	2.3	2.3	2.3	2.3	2.3	2.3
Dissipation Factor (ASTM D 150)	.002	.001	.001	.001	.001	.001
Dielectric Strength (ASTM D 149)	1400 volts/mil (11 mil sample)					
Volume Resistivity (ASTM D 257)	6.0 x 10 ¹⁷ ohm-cm					
Surface Resistivity (ASTM D 257)	4.5 x 10 ¹⁷ ohm/sq.					

Typical Corrosion Properties

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Per ASTM D 3482 (35°C/96% RH/45 v.d.c/15 days)	Pass – No electrolytic corrosion.
Per TM C 708* (45°C/96% RH/250 v.d.c/5 days)	Pass – No electrolytic corrosion. Very minor surface oxidation of test wire.
Per Mil S-46163 (10 days/50% RH/23°C)	Pass – No aluminum, brass or steel corrosion or discoloration.

*Test involves placing two #36 AWG (.005") oxygen free bare copper wires on clean 1" x 4" glass slides in fixed position 1/4" apart. Adhesive is coated over the wires and over the area between the wires in a uniform manner and cured/set. The test specimen is then subjected to 45°C / 96% relative humidity / 250 volts d.c. for 5 days. The aged specimen is then visually examined for corrosion/attack of the copper surface

Typical Solvent Resistance

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

	1 Hour	30 Days
Acetone	A	B
Isopropyl Alcohol	A	B
Freon® TF	B	C
Freon® TMC	B	C
1, 1, 1 - trichloroethylene	B	C
RMA Flux	A	B

Key: A = No attack
 B = Slight Surface Attack/Softness
 C = Severe Attack/Breakup

3M™ Jet-melt™ Self-Extinguishing Hot Melt Adhesive 3748 VO

Storage Store below 120°F (49°C).


Shelf Life 12 months from the date of manufacture if stored below 120°F (49°C).

Precautionary Information Refer to Product Label and Material Safety Data Sheet for health and safety information before using this product. For additional health and safety information, call 1-800-364-3577 or (651) 737-6501.

For Additional Information To request additional product information or to arrange for sales assistance, call toll free 1-800-362-3550 or visit www.3M.com/adhesives. Address correspondence to: 3M Industrial Adhesives and Tapes Division, Building 21-1W-10, 900 Bush Avenue, St. Paul, MN 55106. Our fax number is 651-733-9175. In Canada, phone: 1-800-364-3577. In Puerto Rico, phone: 1-787-750-3000. In Mexico, phone: 52-70-04-00.

Important Notice 3M MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. User is responsible for determining whether the 3M product is fit for a particular purpose and suitable for user's application. Please remember that many factors can affect the use and performance of a 3M product in a particular application. The materials to be bonded with the product, the surface preparation of those materials, the product selected for use, the conditions in which the product is used, and the time and environmental conditions in which the product is expected to perform are among the many factors that can affect the use and performance of a 3M product. Given the variety of factors that can affect the use and performance of a 3M product, some of which are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's application.

Limitation of Remedies and Liability If the 3M product is proved to be defective, THE EXCLUSIVE REMEDY, AT 3M'S OPTION, SHALL BE TO REFUND THE PURCHASE PRICE OF OR TO REPAIR OR REPLACE THE DEFECTIVE 3M PRODUCT. 3M shall not otherwise be liable for loss or damages, whether direct, indirect, special, incidental, or consequential, regardless of the legal theory asserted, including, but not limited to, contract, negligence, warranty, or strict liability.



This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9002 standards.



**Industrial Business
Industrial Adhesives and Tapes Division**
3M Center, Building 21-1W-10, 900 Bush Avenue
St. Paul, MN 55106



*Recycled Paper
40% pre-consumer
10% post-consumer*

Freon is a registered trademark of
E.I. DuPont de Nemours Co.
Printed in U.S.A.
©3M 2003 78-6900-9915-1 (2/03)